



TECHNICAL SPECIFICATION SHEET

ARTICLE NAME: **SELENE**

RAW MATERIAL: **OX/BULL NEW ZEALAND**

AVERAGE SIZE: **4.50 m²**

THICKNESS: **ca. 1.0 mm**

Test	Test method	Result
1. Colour fastness to rubbing: Nr. 50 dry rubs Nr. 20 wet rubs Nr. 20 alkaline ph 8	IUF 450 / UNI EN ISO 11640 IUF 450 / UNI EN ISO 11640 IUF 450 / UNI EN ISO 11640	N/A N/A N/A
2. Flexing endurance	IUP 20 UNI EN ISO 5402	≥ 30.000
3. Tear strength	IUP 40 UNI EN ISO 3377-1	≥ 20 N
4. Adhesion	IUF 470 UNI EN ISO 11644	≥ 3.50 N/cm
5. Light resistance (xenon test)	IUF 402 UNI EN ISO 105-B02	3 blue scale

All our leathers comply with the strict regulations and EU Directives covering the use and presence of PCP, CFC, Chromo VI and Azo dyestuffs during the tanning process.
Due to the natural properties of leather colour variations between one dye lot and another may occur.

Vicolo Marconi, 1 36071 ARZIGNANO (VI), Italy
Tel. +39 0444 451455 Telefax +39 0444 451832
e-mail: futura@futuraleathers.com <http://www.futuraleathers.com>