

PISTA – Slightly corrected semi aniline

Technical specifications

Average size: 4,5m²
Thickness: 0,8-1,0mm

Raw material: European and North American rawhides
Tanning: Chrome tanned



	Method	Test result
Light fastness	DIN EN ISO 105-B02 / IUF 402	3
Rubbing fastness – dry - 100 rubbings	DIN EN ISO 11640 / IUF450	≥4
Rubbing fastness – wet - 40 rubbings	DIN EN ISO 11640 / IUF450	≥4
Rubbing fastness – sweat - 20 rubings	DIN EN ISO 11640 / IUF450	≥4
Tear strenght	DIN EN ISO 3377-1 / UIP 40	≥20 N
Flexing endurance	DIN EN ISO 5402 / IUP20	≥20.000

All CAMO leather is dyed through and produced without use of PCP and CFC.
Our leather does not contains chrome VI.
All articles observe the standards for the REACH declaration.