

# BIZON – corrected leather

## Technical specifications

Average size: 4,5m<sup>2</sup>  
Thickness: 1,2-1,4mm

Raw material: Overseas raw hides  
Tanning: Chrome tanning



	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥7
Rubbing fastness – dry, colour changes, 500 rubbings	DIN EN ISO 11640	5
Rubbing fastness – dry, smudging, 500 rubbings	DIN EN ISO 11640	4
Rubbing fastness – wet, colour changes, 250 rubbings	DIN EN ISO 11640	4
Rubbing fastness – wet, smudging, 250 rubbings	DIN EN ISO 11640	2-3
Rubbing fastness – perspiration, colour changes, 80 rubbings	DIN EN ISO 11640/41	4-5
Rubbing fastness – perspiration, smudging, 80 rubbings	DIN EN ISO 11640/41	3-4
Adhesion of finish	DIN EN ISO 11644	6,0 N/10mm
Dry flexing resistance	DIN EN ISO 5402	≥200.000

### Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 1990 Sec. 4 NI/0-1,

California T.B.117

All CAMO leather is dyed through and produced without use of PCP and CFC.

Our leather does not contain chrome VI.

All articles observe the standards for the REACH declaration.