

# SEVILLA – Slightly corrected semi aniline

## Technical specifications

Average size: 5-6 m<sup>2</sup>  
Thickness: 1,1-1,3 mm

Raw material: Brazilian rawhides  
Tanning: Chrome tanned



	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥4
Rubbing fastness – dry - 500 rubbings	DIN EN ISO 11640	4
Rubbing fastness – wet - 150 rubbings	DIN EN ISO 11641	4
Rubbing fastness – sweat - 80 rubbings	DIN EN ISO 11640	4
Finish Adhesion (dry)	DIN EN ISO 11644	≥3N/cm
Flexing indurance	DIN EN ISO 5402	20000
Tearing strenght	DIN EN ISO 3377-2	≥40 N

### Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS 5852 1991 Sec. 4 NI/0-1

California T.B 117

All CAMO leather is dyed through and produced without use of PCP and CFC.

Our leather does not contain chrome VI.

All articles observe the standards for the REACH declaration.