

PALOMA – light corrected semi aniline

Technical specifications

Average size: 5-6m²
Thickness: 1,0-1,2mm

Raw material: European raw hides
Tanning: Free of chrome



	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥6
Rubbing fastness – dry - 500 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness – wet - 80 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness – sweat - 50 rubbings	DIN EN ISO 11640	≥4
Tear strength	DIN EN ISO 3377-1	≥20 N/mm
Flex endurance	DIN EN ISO 5402	30.000
PH value	DIN ISO 4045	≥3,5
Finish Adhesion	DIN EN ISO 11644 / 5402	≥2,5 N/cm

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 Crib 5

ÖNORM B 3800

DIN 5510-2 "Papierkissen-Test"

ÖNORM B3825 hardly inflammable

IMO-Res. A652 (16)

California T.B 117

All CAMO leather is dyed through and produced without use of PCP and CFC.

Our leather does not contain chrome VI.

All articles observe the standards for the REACH declaration.