

## ALPIN – Semi Aniline leather

### Technical specifications

Average size: 5,0 m<sup>2</sup>  
Thickness: 1,4-1,6 mm

Raw material: South German raw hides  
Tanning: Free of chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥5
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, wet, 80 rubbings	DIN EN ISO 11640	≥4
Tearing strength	DIN EN ISO 3376	≥80 N
Flexing endurance	DIN EN ISO 5402	30.000
PH value	DIN ISO 4045	≥3,5

Chrome free tanned and without the use of PCP and CFC which are damaging to the environment. ALPIN leather is Chrome free (FOC) and complies standard for the REACH declaration.

#### **Flame resistance:**

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 Crib 5

ÖNORM B3800

ÖNORM B3825

DIN 5510-2 "Papierkissen-Test"

IMO-Res. A 652 (16)