

ANDORRA – Semi Aniline leather

Technical specifications

Average size: 4,5 m²
Thickness: 1,0-1,2 mm

Raw material: New Zealand raw hides
Tanning: Chrome tanned

	Method	Test result
Light fastness	DIN EN ISO 105-B02 / IUF402	3
Rubbing fastness, dry, 300 rubbings	DIN EN ISO 11640 / IUF 450	≥ 4
Rubbing fastness, wet, 50 rubbings	DIN EN ISO 11640 / IUF 450	≥ 4
Rubbing fastness, sweat, 30 rubbings	DIN EN ISO 11640 / IUF 450	≥ 4
Adhesion of finish	DIN EN ISO 11644 IUF 470	≥ 3,5 N/cm
Flexing endurance	DIN EN ISO 5402 / IUP 20	≥ 30.000
Tearing strength	IUP 40 / UNI EN ISO 3377-1	≥ 20N

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS 5852 1991 Sec. 4 NI/0-1

California T.B. 117-2013 section 1