

BIZON – Corrected leather

Technical specifications

Average size: 5 m²

Thickness: 1,2-1,4 mm

Raw material: Overseas raw hides

Tanning: Chrome tanning

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥7
Rubbing fastness, dry, colour changes, 500 rubbings	DIN EN ISO 11640	5
Rubbing fastness, dry, smudging, 500 rubbings	DIN EN ISO 11640	4
Rubbing fastness, wet, colour changes, 250 rubbings	DIN EN ISO 11640	4
Rubbing fastness, wet, smudging, 250 rubbings	DIN EN ISO 11640	2-3
Rubbing fastness, perspiration, colour changes, 80 rubbings	DIN EN ISO 11640/41	4-5
Rubbing fastness, perspiration, smudging, 80 rubbings	DIN EN ISO 11640/41	3-4
Adhesion of finish	DIN EN ISO 11644	6,0 N/10mm
Dry flexing resistance	DIN EN ISO 5402	≥200.000

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 1990 Sec. 4 NI/0-1,

California T.B.117-2013 section 1