

BOLERO – Slightly Corrected Semi Aniline

Technical specifications

Average size: 4,20 m²

Thickness: 0,9-1,1 mm

Raw material: Australian or North American rawhides

Tanning: Chrome tanned

	Method	Test result
Light fastness	DIN EN ISO 105-B02 / IUF 402	5
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640 / IUF 450	≥4
Rubbing fastness, wet, 150 rubbings	DIN EN ISO 11640 / IUF 450	≥4
Rubbing fastness, sweat, 80 rubbings	DIN EN ISO 11640 / IUF 450	≥4
Flexing indurance	DIN EN ISO 5402 / IUP 20	≥30.000
Tearing strenght	DIN EN ISO 3377-1 / IUP 40	≥20N

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 1990 Sec. 4 NI/0-1,

California T.B.117