

PALOMA – Light Corrected Semi Aniline

Technical specifications

Average size: 5 m²

Thickness: 1,0-1,2 mm

Raw material: European raw hides

Tanning: Free of chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥6
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, wet, 80 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, sweat, 50 rubbings	DIN EN ISO 11640	≥4
Tear strength	DIN EN ISO 3377-1	≥20 N/mm
Flex endurance	DIN EN ISO 5402	30.000
PH value	DIN ISO 4045	≥3,5
Finish Adhesion	DIN EN ISO 11644 / 5402	≥2,5 N/cm

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 Crib 5

ÖNORM B 3800

DIN 5510-2 "Papierkissen-Test"

ÖNORM B3825 hardly inflammable

IMO-Res. A652 (16)

California T.B 117-2013 section 1