

PISTA – Light Corrected Semi Aniline

Technical specifications

Average size: 4,5 m²

Thickness: 0,8-1,0 mm

Raw material: European or North American rawhides

Tanning: Chrome tanned

	Method	Test result
Light fastness	DIN EN ISO 105-B02 / IUF 402	3
Rubbing fastness, dry, 100 rubbings	DIN EN ISO 11640 / IUF450	≥4
Rubbing fastness, wet, 40 rubbings	DIN EN ISO 11640 / IUF450	≥4
Rubbing fastness, sweat, 20 rubings	DIN EN ISO 11640 / IUF450	≥4
Tear strenght	DIN EN ISO 3377-1 / UIP 40	≥20 N
Flexing endurance	DIN EN ISO 5402 / IUP20	≥20.000

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.