

REGINA – Light Corrected Semi Aniline

Technical specifications

Average size: 5,2 m²
Thickness: 1,2-1,4 mm

Raw material: Grain leather from European raw hides
Tanning: Chrome tanning

	Method	Test result
Light fastness	UNI EN ISO 105-B02	≥4
Rubbing fastness, dry, 500 rubbings	UNI EN ISO 11640	≥3
Rubbing fastness, wet, 150 rubbings	UNI EN ISO 11640	≥3
Rubbing fastness, sweat, 50 rubbings	UNI EN ISO 11640	≥3
Adhesion of finish	UNI EN ISO 11644: 2009	6,1 N/Cm
Dry flexing resistance	UNI EN ISO 5402	≥20.000
Tear strength	UNI EN ISO 3377-1	≥20N

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 1990 Sec. 4 NI/0-1,

California T.B.117-2013 section 1