

SIENA – Corrected leather

Technical specifications

Average size: 5,0 m²
Thickness: 0,9-1,1 mm

Raw material: European raw hides
Tanning: Chrome tanning

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥5
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640	≥5
Flexing endurance	DIN EN ISO 5402	30.000
Tear strength	DIN EN ISO 3377-1	≥20 N/mm

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfils the requirements according to:

UNI EN ISO 1021 – 1/2

BS 5852 crib 5

California T.B. 117-2013 section 1