

SILK – Aniline leather

Technical specifications

Average size: 4,5-5 m²

Thickness: 1,0-1,2 mm

Raw material: European raw hides

Tanning: Chrome tanned

	Method	Test result
Light fastness	DIN EN ISO 105-B02 / IUF 402	3
Rubbing fastness, dry, 100 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, wet, 20 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, sweat, 20 rubbings	DIN EN ISO 11640	≥4
Flexing endurance	DIN EN ISO 5402-1 / IUP 20	≥30.000
Tearing strength	DIN EN ISO 3377-1 / IUP 40	≥20 N/mm
Adhesion of finish	DIN EN ISO 11644 / IUF 470	≥3,50 N/cm

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

BS5852:1979 UK Match & Cigarette test

California T.B. 117-2013 section 1