

## VACONA® – Aniline leather

### Technical specifications

Average size: 6,0 m<sup>2</sup>  
Thickness: 1,0-1,2 mm

Raw material: South German raw hides  
Tanning: Chrome tanning

|                                    | Method             | Test result |
|------------------------------------|--------------------|-------------|
| Light fastness                     | DIN EN ISO 105-B02 | ≥3          |
| Rubbing fastness, dry, 50 rubbings | DIN EN ISO 11640   | ≥3          |
| Rubbing fastness, wet, 20 rubbings | DIN EN ISO 11640   | ≥3          |
| Tear Strength                      | DIN EN ISO 3377-1  | ≥20 N/mm    |
| Flexing Endurance                  | DIN EN ISO 5402    | 20.000      |

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

#### **Flame resistance:**

The material fulfils the requirements according to:

UNI EN ISO 1021 – 1/2

BS5852 Crib 5

California T.B. 117-2013 section 1