

SYDNEY – Light Corrected Semi Aniline

Technical specifications

Average size: 4,2 m²
Thickness: 0,9-1,1 mm

Raw material: Grain leather from Australia, New Zealand, or European raw hides
Tanning: Chrome tanning

| | Method | Test result |
|---|------------------------------|-------------|
| Light fastness | IUF 402 / DIN EN ISO 105-B02 | 5 |
| Rubbing fastness, dry, 500 rubbings | IUF 450 / DIN EN ISO 11640 | ≥4 |
| Rubbing fastness, wet, 150 rubbings | IUF 450 / DIN EN ISO 11640 | ≥4 |
| Rubbing fastness, perspiration, 80 rubbings | IUF 450 / DIN EN ISO 11640 | ≥4 |
| Adhesion of finish | IUF 470 / DIN EN ISO 11644 | 3,5 N/Cm |
| Tear strength | IUP 40 / UNI EN ISO 3377-1 | ≥20 N |
| Flexing endurance | IUP 20 / DIN EN ISO 5402 | 30.000 |

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 1991 Sec. 4 NI/0-1,

California T.B.117