

ALABAMA – Aniline leather

Technical specifications

Average size: 6,0 m²
Thickness: 1,1-1,3 mm

Raw material: South German raw hides
Tanning: Chrome tanned

	Method	Test result
Light fastness	DIN EN ISO 105-B02	3
Rubbing fastness, dry, 50 rubbings	DIN EN ISO 11640	≥3
Rubbing fastness, wet, 20 rubbings	DIN EN ISO 11640	≥3
Rubbing fastness, sweat, 20 rubbings	DIN EN ISO 11640	≥3
Tearing strength	DIN EN ISO 3377-1	≥20 N/mm
Flexing endurance	DIN EN ISO 5402-1	≥20.000
PH value	DIN EN ISO 4045	≥3,3

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flammability test:

The material fulfils the requirements according to:
California T.B. 117-2013 section 1
UNI EN ISO 1021 – 1/2

