

GENOVA – Aniline leather

Technical specifications

Average size: 6,0 m²
Thickness: 1,0-1,2 mm

Raw material: South German raw hides
Tanning: Chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02 / IUP20	≥3
Rubbing fastness, dry, 50 rubbings	DIN EN ISO 11640 / IUF 450	≥3
Rubbing fastness, wet, 20 rubbings	DIN EN ISO 11640/ IUF 450	≥3
Rubbing fastness, sweat, 20 rubbings	DIN EN ISO 11640/ IUF 450	≥3
Flexing endurance	DIN EN ISO 5402-1	20.000
Tearing strength	DIN EN ISO 3377-1	≥20 N/mm
PH value	DIN EN ISO 4045	≥3,5

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirements according to:

UNI EN ISO 1021-1/2

BS 5852 Crib 5

California T.B. 117-2013 section 1