

## **KENYA – Vintage Aniline leather**

### Technical specifications

Average size: 5,5 m<sup>2</sup>

Thickness: 1,0-1,1 mm

Raw material: European raw hides

Tanning: Chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥3
Rubbing fastness, dry, 50 rubbings	DIN EN ISO 11640	≥3
Rubbing fastness, wet, 20 rubbings	DIN EN ISO 11640	≥3
Tearing strenght	DIN EN ISO 3377-1	≥20 N
Flexing indurance	DIN EN ISO 5402	≥30.000

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

#### **Flame resistance:**

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 1990 Sec. 4 NI/0-1,