

SIERRA – Corrected leather

Technical specifications

Average size: 5,0 m²
Thickness: 0,9-1,1 mm

Raw material: Overseas raw hides
Tanning: Chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥4
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640/41	4
Rubbing fastness, wet, 250 rubbings	DIN EN ISO 11640/41	4
Rubbing fastness, perspiration, 80 rubbings	DIN EN ISO 11640/41	4
Adhesion of finish	DIN EN ISO 11644	3 N/cm
Tear strength	DIN EN ISO 3377-2	≥ 40 N
Dry flexing resistance	DIN EN ISO 5402-1	50.000
PH value	DIN EN ISO 4045	≥ 3,2

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS 5852 1991 Sec. 4 NI/0-1,

California T.B.117-2013 section 1