

## VACONA® – Aniline leather

### Technical specifications

Average size: 6,0 m<sup>2</sup>  
Thickness: 1,0-1,2 mm

Raw material: South German raw hides  
Tanning: Chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥3
Rubbing fastness, dry, 50 rubbings	DIN EN ISO 11640	≥3
Rubbing fastness, wet, 20 rubbings	DIN EN ISO 11640	≥3
Tear Strength	DIN EN ISO 3377-1	≥20 N/mm
Flexing Endurance	DIN EN ISO 5402	20.000

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

#### **Flame resistance:**

The material fulfils the requirements according to:

UNI EN ISO 1021 – 1/2

BS5852 Crib 5

California T.B. 117-2013 section 1