

VICTORIA – Aniline leather

Technical specifications

Average size: 5,5 m²
Thickness: 1,3-1,5 mm

Raw material: European raw hides
Tanning: Chrome

	Method	Test result
Light fastness	UNI EN ISO 105-B02	>3
Rubbing fastness, dry, 50 rubbings	UNI EN ISO 11640	>3
Rubbing fastness, wet, 20 rubbings	UNI EN ISO 11640	>3
Rubbing fastness, sweat, 10 rubbings	UNI EN ISO 11640	>3
Tearing strength	UNI EN ISO 3377-1	> 20 N/mm

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfils the requirements according to:
according to:

UNI EN ISO 1021 – 1/2

BS 5852 1991 Sec. 4 NI/0-1

California T.B. 117-2013 Section 1