

MAMMUT – Corrected leather

Technical specifications

Average size: 4,8 m²
 Thickness: 0,9-1,3 mm

Raw material: European raw hides
 Tanning: Chromefree

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥6
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, wet, 80 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, sweat, 50 rubbings	DIN EN ISO 11640	≥4
Tearing strength	DIN EN ISO 3377-1	≥20 N/mm
Flexing endurance	DIN EN ISO 5402	30.000
Finish Adhesion	DIN EN ISO 11644 / 5402	≥2,5 N/cm
PH value	DIN ISO 4045	≥3,5

Chrome free tanned and without the use of PCP and CFC which are damaging to the environment. MAMMUT leather is Chrome free (FOC) and complies standard for the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 Crib 5

ÖNORM B3800

ÖNORM B3825

DIN 5510-2 "Papierkissen-Test"

IMO-Res. A 652 (16)

California T.B. 117-2013 section 1