

AMBASSADOR – Aviation Leather

Technical specifications

Average size: 5,0 m²
Thickness: 0,9-1,3 mm

Raw material: European rawhides
Tanning: Chrome free tanned

	Method	Test result
Light fastness	VDA 75202 Xenotest	6-7
Rubbing fastness, dry, 2.000 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, wet, 500 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, sweat, 50 rubbings	DIN EN ISO 11640	≥4
Tearing strength	DIN EN ISO 3377-1	≥20 N
Flexing endurance	DIN EN ISO 5402	≥30.000
Adhesion of finish	ISO 11644	≥3,0 N/Cm

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flammability test:

The material fulfils the requirements according to:

UNI EN ISO 1021 – 1/2,

IMO-Res. A 652 (16)

ÖNORM B3825 hardly inflammable

ÖNORM B3800 Smoke density / Dripping

DIN 5510-2 “Papierkissen-Test”

California T.B. 117-2013 section 1

