

IMPERIA – Aniline leather

Technical specifications

Average size: 4,8 m²
Thickness: 1,3-1,5 mm

Raw material: European bull hides
Tanning: Corn tanned (chrome and metal free)

	Method	Test result
Light fastness	DIN EN ISO 105-B02	2/3
Rubbing fastness, dry, 80 rubbings	DIN EN ISO 11640	≥3
Rubbing fastness, wet, 20 rubbings	DIN EN ISO 11640	≥3
Rubbing fastness, sweat, 80 alkaline Ph 8	DIN EN ISO 11640	≥3
Tearing strength	DIN EN ISO 3377-1	≥20 N
Flexing endurance	DIN EN ISO 5402-1	20.000 no cracking

Corn tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for metal and chrome free tanning and the REACH declaration.

Flammability test:

The material fulfils the requirements according to:
UNI EN ISO 1021-1/2

BS 5852/0 - Cigarette test

BS 5852/1 – Match test

BS 5852 Crib 5

California T.B. 117-2013 section 1