

BARI – Vintage Aniline leather

Technical specifications

Average size: 4,2 m²
Thickness: 0,9-1,1 mm

Raw material: New Zealand rawhides
Tanning: Chrome

	Method	Test result
Light fastness	IUF 402 / DIN EN ISO 105-B02	3
Rubbing fastness, dry, 50 rubbings	IUF 450 / DIN EN ISO 11640	4
Rubbing fastness, wet, 10 rubbings	IUF 450 / DIN EN ISO 11640	4
Rubbing fastness, sweat, 10 rubbings	IUF 450 / DIN EN ISO 11640	4
Tearing strenght	IUF 40 / DIN EN ISO 3377-1	≥20 N
Adhesion of finish	IIUF 470 / UNI EN ISO 11644	≥3,50 N/cm

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment.

The leather complies with all limits and standards for chrome VI and the REACH declaration.