

ONE – Vintage Leather

Technical details

Average size: ca. 4,50 m²

Thickness: 0,9-1,1 mm

Origin: New Zealand cowhides

Tannage: Chrome

	Method	Test result
Light resistance	IUF 402 / UNI EN ISO 105-B02	3 blue scale
Rubbing resistance, dry, 50 rubbings	IUF 450 / UNI EN ISO 11640	≥ 4 grey scale
Tear strength	IUP 40 / UNI EN ISO 3377-1	≥ 20 N
Flexing endurance	IUP 20 / UNI EN ISO 5402	≥ 30.000

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfils the requirements according to:

UNI EN ISO 1021 – 1/2

BS 5852 1991 Sec. 4 NI/0-1

California T.B. 117