

TUNDRA – Aniline leather

Technical specifications

Average size: 4,5 m²

Thickness: 1,2-1,4 mm

Raw material: Australian rawhides

Tanning: Chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02 / IUF 402	3
Rubbing fastness, dry, 100 rubbings	DIN EN ISO 11640 / IUF 450	4
Rubbing fastness, wet, 10 rubbings	DIN EN ISO 11640 / IUF 450	4
Rubbing fastness, sweat, 10 rubbings	DIN EN ISO 11640 / IUF 450	4
Tearing strength	DIN EN ISO 3377-1	Min. 20 N/mm

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021 – 1/2

BS 5852 1991 Sec. 4 NI/0-1

CALIFORNIA T.B. 117-2013 section 1